

GELCOAT IN-700 (clear) is a premium quality gelcoat. It is enhanced UV-resistant decorative coating based on ISO/NPG unsaturated polyester resin, for “spray” (**GELCOAT IN-700 S**) and “hand” application (**GELCOAT IN-700 H**). The gelcoat could be tinted to any colour in accordance with RAL catalogue or with your laminate sample.

1. BASIC CHARACTERISTICS AND APPLICATION AREA

Gelcoat is very effective when it is used in manufacturing of products that are exposed to weather, water and slightly aggressive chemicals at different temperatures.

Application:

- Production of the first decorative layer of laminated flooring
- Production of bathroom and lavatory equipment
- Production of facade elements
- Production of car parts
- Production of boats

Correct application is the key factor of getting a nice and high-quality product. Gelcoat is applied in order to give a necessary color and gloss and protective properties to the product. Temperature of equipment and materials should be 20-23°C. Recommended peroxide dose is 1,3-2,0%.

2. RESIN DELIVERY CHARACTERISTICS

Properties	“For spray” brand	“For hand” brand	Units	Testing method
	GELCOAT IN-700S	GELCOAT IN-700H		
1. Appearance	Slight opalescence without mechanical impurities	Slight opalescence without mechanical impurities	-	Visual
2. Solid matters content	57±2	57±2	%	ISO 3251
3. Brookfield viscosity, 23°C; spindle 4; speed 12	5000-7500	10000-20000	mPa·s	ISO 2555
4. Density, 20°C	1,13±0,05	1,13±0,05	g/cm ³	ISO 2811
5. Gel time, 20°C 1,5% MEKP (50%)	18-25	18-25	min.	ISO 2535

* Gel time can be changed by the customer’s request.

3. STANDARD PACKAGING

20 kg metal buckets.

4. STORAGE

Shelf life 4 months

Storage conditions it should be stored indoors at 25°C in its original packaging, it should be kept away from direct sunlight

www.dugalak.com

D.O.O. Dugalak, Serbia

Sales: 11000 Belgrade, Bul.Arsenija Carnojevicica 101

Phone: +381 11 711 9590

E-mail: ivana.stanistic@dugalak.com

Technical support:

Phone: +381 60 389 0180, +7 962 212 37 42

E-mail: d.zivkovic@dugalak.ru