

**DEPOL SR-700RMP** - Middle reactive, pre-promoted, low-viscosity terephthalic and orthophthalic acid based resin.

## 1. MAIN CHARACTERISTICS AND AREA OF APPLICATION

Used for production of parts for automobiles and water transport, auto-tuning elements, small boats, decorative panels, with application of PTM and Light PTM technologies and use of high-density glass mats.

Advantages:

- High mechanical properties;
- Low viscosity allows high-speed filling of the matrix, which is reflected in productivity, and also ensures an even filling of the matrix;
- Excellent wetting of the glass material inserted into the matrix;
- The resin is fairly reactive and ensures quick hardening and gain of solidity;
- Low exotherm peak.

Handle the resin at room temperature using the accelerator-hardener system (cobalt octoate - MEKP).

## 2. CHARACTERISTICS IN DELIVERY FORM

Properties	Unit of measurement	Indicator	Method
1. Appearance		Transparent liquid without additional additives	Visual
2. Solid matters content	%	54-58	ISO 3251
3. Brookfield viscosity 12/2 at 23°C	mPa*s	170-200	ISO 2555-89
4. Gel time* at temperature of 20°C, 1,5% MEKP (50%) (Butanox M-50)	min	30/60/120	ISO 2535-74

## 3. STANDARD PACKAGING

220kg steel/tin drums, with two plugs, 1100kg polyethylene cubes



## 4. STORAGE

**Shelf life:** 4 months

**Storage conditions:** in original packaging, stored indoors, not exposed to direct sunlight, at the temperature below 25°C.



[www.dugalak.ru](http://www.dugalak.ru)

*E-Mail: [dugalak@nordnet.ru](mailto:dugalak@nordnet.ru)*

Sales office: (4852) 73-37-64, 73-37-01; technical support: (8 901) 985-33-24