

DEPOL IN-200 is a middle reactive, modified by acrylate, non-thixotropic, unsaturated, isophthalic acid and neopentyl glycol dissolved in styrol based polyester resin of medium viscosity.

1. BASIC CHARACTERISTICS AND APPLICATION AREA

Due to its good mechanical, thermal and electric properties and also weather resistance it is commonly used in Solid Surface production.

It is a UV-resistant resin of high quality. This resin has high hardness, gloss and is resistant to heat impact.

Working with resin requires room temperature and using of accelerator-hardener system (cobalt octoate – MEKP).

2. RESIN DELIVERY CHARACTERISTICS

Properties	Unit	Value	Method
1. Appearance		Transparent liquid without mechanical impurities	Visual
2. Non-volatile-matter content	%	65±2	GOST P 52487 and p. 4.4. of Technical Specification
3. Dynamic Brookfield viscosity 23°C; spindle 2; speed 12	mPa.s	800-1300	GOST 25271-93
4. Acid value	mgKOH/g	15-25	ISO 3682
5. Density 20°C	g/cm ³	1,1±0,05	GOST 18329 and p. 4.3 of Technical Specification
6. Gel time 2% of Butanox M-50	minutes	9-16	GOST 22181 and p. 4.5 of Technical Specification
7. Flash point	°C	31	ISO 3679

3. STANDARD PACKAGING

220 kg two-plugs metal barrels, 1000 kg IBC.

4. STORAGE

Shelf life 6 months
Storage conditions resin should be stored indoors at 25°C or below in its original packaging, it should be kept away from direct sunlight

www.dugalak.com

D.O.O. Dugalak, Serbia

Sales: 11000 Belgrade, Bul.Arsenija Carnojevica 101

Phone: +381 11 711 9590

E-mail: ivana.stanistic@dugalak.com

Technical support:

Phone: +381 60 389 0180, +7 962 212 37 42

E-mail: d.zivkovic@dugalak.ru