

## DEPOL PT-700GTF

Middle reactive, non-promoted, non-thixotropic unsaturated terephthalic based polyester resin.

### 1. MAIN CHARACTERISTICS AND AREA OF APPLICATION

Used for production of chemically resistant fiberglass.

Handle the resin at room temperature using the accelerator-hardener system (cobalt octoate - MEKP).

### 2. CHARACTERISTICS IN DELIVERY FORM

Properties	Unit of measurement	Indicator	Method
1. Appearance		Blue liquid, without mechanical additives	Visual
2. Solid matters content	%	60±2	ISO 1515
3. Brookfield viscosity 2/12 at 23°C	mPa*s	450±100	ISO 2431
4. Acid number	mgKOH/g	15	ISO 3682
5. Gel time: 2g Co 1% 3g of Butanox M-50	min	20-30	ISO 2535-74
6. Peak temperature	°C	31	ISO 3679

### 3. STANDARD PACKAGING

220 kg steel/tin drums, with two plugs

IBC containers 1000 litres

### 4. STORAGE

**Shelf life:** 6 months

**Storage conditions:** in original packaging, stored indoors, not exposed to direct sunlight, at the temperature below 25°C.

DUGALAK LLC Yaroslavl, Russian Federation

Moscow office (Export import department)

[zpavlovic@dugarus.ru](mailto:zpavlovic@dugarus.ru) +7499 124 09 12

[www.dugalak.ru](http://www.dugalak.ru)

